

Lightfastness Tapetex Wall Materials 65 - Silk / Silky

E.031711B.v3

Testing as per ISO 105-B02:2014

Testresults are based upon 216 hours of exposure. The test was stopped at 216 hours.

Location test : Tapetex BV, Helmond, The Netherlands
Testing machinery : Heraeus original Hanau Xenotest 150S
Standard blue scale 0 - 8
Humidity 65%, Blackpanel temperature 45° Celsius

Tapetex 65 - Silk/Silky

Lightfastness

65-1250	6	65-1271	7	65-1302	5	65-1333	6	65-1374	7
65-1251	6	65-1272	6	65-1303	6	65-1334	5	65-1375	7
65-1252	6	65-1273	6	65-1304	5	65-1340	7	65-1376	7
65-1253	6	65-1274	6	65-1310	5	65-1341	7	65-1377	7
65-1254	6	65-1275	5	65-1311	5	65-1342	7	65-1378	7
65-1255	6	65-1276	5	65-1312	5	65-1343	7	65-1379	7
65-1256	6	65-1277	6	65-1313	5	65-1344	7	65-1380	7
65-1257	6	65-1278	4	65-1314	5	65-1350	7	65-1381	7
65-1258	6	65-1279	6	65-1315	5	65-1351	7	65-1382	7
65-1259	4	65-1280	6	65-1316	5	65-1352	7	65-1383	7
65-1260	7	65-1281	7	65-1317	5	65-1353	7	65-1384	7
65-1261	7	65-1282	7	65-1318	6	65-1354	7	65-1390	5
65-1262	7	65-1283	6	65-1319	6	65-1360	7	65-1391	5
65-1263	6	65-1284	5	65-1320	6	65-1361	7	65-1392	5
65-1264	7	65-1290	3	65-1321	6	65-1362	7	65-1393	5
65-1265	5	65-1291	7	65-1322	6	65-1363	7	65-1394	5
65-1266	6	65-1292	6	65-1323	6	65-1364	7	65-1400	6
65-1267	6	65-1293	4	65-1324	6	65-1370	7	65-1401	6
65-1268	6	65-1294	6	65-1330	7	65-1371	7	65-1402	6
65-1269	3	65-1300	7	65-1331	7	65-1372	7	65-1403	6
65-1270	7	65-1301	7	65-1332	6	65-1373	7	65-1404	6