

Lightfastness Tapetex Wall Materials - 64 - Linen

E.031711A.v1

Testing as per ISO 105-B02:2014

Testresults are based upon 216 hours of exposure. The test was stopped at 216 hours.

Location test : Tapetex BV, Helmond, The Netherlands

Testing machinery : Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Golden Flax	4	64-1074
	5	64-1070 - 64-1073
	6	64-1071 - 64-1072
Casalin	5	64-1081
	6	64-1080 - 64-1082 / 64-1084
Montalin	6	64-1090 / 64-1099
Espalin	4	64-1100 - 64-1102 - 64-1103
	6	64-1101
Spica	4	64-1104
Puntolin	6	64-1105 / 64-1109
Linum	4	64-1114
	5	64-1110 - 64-1112 - 64-1113
	6	64-1111
Linolin	5	64-1121 / 64-1127
	6	64-1120 - 64-1128 - 64-1129
Irish Heritage	4	64-1134
	5	64-1130
	6	64-1131 / 64-1133
Ringolin	6	64-1135 / 64-1139
Muralin	6	64-1140 / 64-1149
Mesalin	5	64-1150 - 64-1151
	6	64-1152 - 64-1159
Artilin	6	64-1160 / 64-1169

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Linola	5	64-1170
	6	64-1171 / 64-1174
Terralin	6	64-1180 / 64-1189
Lin Titania	5	64-1200 / 64-1204