

Lightfastness Tapetex Wall Materials - 65 - Silk / Silky

E.031711B.v1

Testing as per ISO 105-B02:2014

Testresults are based upon 216 hours of exposure. The test was stopped at 216 hours.

Location test : Tapetex BV, Helmond, The Netherlands

Testing machinery : Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Chandra Silk	3	65-1269
	4	65-1259 - 65-1278
	5	65-1265 - 65-1275 / 65-1276
	6	65-1252 / 65-1258 - 65-1263 - 65-1266 - 65-1267 - 65-1269 - 65-1272 - 65-1273 - 65-1277 - 65-1279
	7	65-1260 / 65-1262 - 65-1264 - 65-1270 - 65-1271
Shambala Silk	5	65-1284
	6	65-1280 - 65-1283
	7	65-1281 - 65-1282
Ayesha Silk	3	65-1290
	4	65-1293
	6	65-1292 - 65-1294
	7	65-1291
Lost Horizon Silk	5	65-1302 - 65-1304
	6	65-1303
	7	65-1300 - 65-1301
Saray Silk	5	65-1310 / 65-1317
	6	65-1318 - 65-1319
Tabaz Silk	6	65-1320 - 65-1324
Sagar Silk	5	65-1334
	6	65-1332 - 65-1333
	7	65-1330 - 65-1331
Chateau Chinon Silky	7	65-1340 / 65-1344
Chennai Silky	7	65-1350 / 65-1354
New Voyages Silky	7	65-1360 / 65-1364
Madurai Silky	7	65-1370 / 65-1379

---

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Deep Spaces Silky	7	65-1380 / 65-1384
Kerala Silky	5	65-1390 / 65-1394
Princess Lace Silky	6	65-1400 / 65-1404