

Lightfastness Tapetex Wall Materials - 66 - Textiles Variety

E.031711C.v1

Testing as per ISO 105-B02:2014

Testresults are based upon 216 hours of exposure. The test was stopped at 216 hours.

Location test : Tapetex BV, Helmond, The Netherlands

Testing machinery : Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Smooth Sheen	5	66-1413
	6	66-1410 / 66-1412 - 66-1414
	7	66-1415 - 66-1416
Hexagon Inspiration	5	66-1425 - 66-1426
	6	66-1420 - 66-1424
	7	66-1421 - 66-1422 - 66-1423
Bradford Wool	5	66-1433 - 66-1434 - 66-1437 - 66-1438
	6	66-1430 - 66-1431 - 66-1432 - 66-1435 - 66-1436 - 66-1439
Bandra Wild Silk	6	66-1440 - 66-1442 / 66-1449
	7	66-1441
Ventura	6	66-1450 - 66-1454 / 66-1458
	7	66-1451 / 66-1453 - 66-1459
Raffia Decor	6	66-1460 - 66-1464 / 66-1467
	7	66-1461 / 66-1463 - 66-1468 - 66-1469
Luxury Composition	5	66-1470 / 66-1472 - 66-1476
	6	66-1473 / 66-1475
Normandy	7	66-1480 / 66-1486
Crafty Deformation	5	66-1503
	6	66-1500 - 66-1502 - 66-1504 / 66-1509
	7	66-1501
Mechanical Workmanship	7	66-1510 / 66-1519
Orissa	5	66-1525 / 66-1529
	6	66-1520 / 66-1524
Brittany	6	66-1530 / 66-1533 - 66-1535 / 66-1539
	7	66-1534

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Relief Repetition	6	66-1540
	7	66-1541 / 66-1549
Picardy	7	66-1550 / 66-1556
Venetian Heritage	6	66-1560 / 66-1563 - 66-1565 - 66-1566
	7	66-1564
Bandol Solid	7	66-1570 / 66-1576
Bandol Metallic	7	66-1577 / 66-1579
Evian	6	66-1582 - 66-1583
	7	66-1580 - 66-1581 - 66-1584
Tech Inspirations	7	66-1600 / 66-1606
Graphic Spirit	5	66-1610 - 66-1612 / 66-1614
	6	66-1611
Belle Epoqie	5	66-1620
	6	66-1621 / 66-1624
Powerfull Connections	5	66-1634
	6	66-1630 - 66-1632 - 66-1633
	7	66-1631
Veneto	5	66-1640 - 66-1647 / 66-1649
	6	66-1641 / 66-1646