

**Fire Retardency Reports on Tapetex Wall Materials - Euroclass**

E.031712A.v2

**Warringtonfiregent, did test the Tapetex Wall Materials as per the Euroclass test-method:**  
EN 13501-1: 2007 + A1 : 2009

The test data are provided for general informational purposes only and do not by itself incorporate all factors required for fire-hazard or fire-risk assessment of products under actual fire conditions.

**The Tapetex Wall Materials were arranged in 7 compositions and 7 reports:**

**1. Tapetex woven textiles of cellulosic fibres (linen, cotton, viscose)**

on a paper backing of 70% woodpulp reinforced with 30% polyester and with a weight of approx. 595 gr/m2. Tested quality 66-1481.

Test-report Warringtonfiregent : 17910/A/B/C, dated August 10, 2016  
Test-result : B s2 d0

**2. Tapetex woven textiles of cellulosic fibres (linen, cotton, viscose) and synthetic fibres (polyester, nylon)**

on a paper backing of 70% woodpulp reinforced with 30% polyester and with a weight of approx. 465 gr/m2. Tested quality 66-1426.

Test-report Warringtonfiregent : 17911/A/B/C, dated August 10, 2016  
Test-result : B s2 d0

**3. Tapetex woven textiles of animal fibres (silk, wool)**

on a paper backing of 70% woodpulp reinforced with 30% polyester and with a weight of approx. 330 gr/m2. Tested quality 66-1521.

Test-report Warringtonfiregent : 17822/A/B/C, dated July 23, 2016  
Test-result : B s1 d0

**4. Tapetex woven textiles of animal fibres (silk, wool) and synthetic fibres (polyester, nylon)**

on a paper backing of 70% woodpulp reinforced with 30% polyester and with a weight of approx. 490 gr/m2. Tested quality 66-1436.

Test-report Warringtonfiregent : 17955/A/B/C, dated September 17, 2016  
Test-result : C s2 d0

**5. Tapetex woven textiles of synthetic fibres (polyester, nylon)**

on a paper backing of 70% woodpulp reinforced with 30% polyester and with a weight of approx. 440 gr/m2. Tested quality 66-1648.

Test-report Warringtonfiregent : 17956/A/B/C, dated September 17, 2016  
Test-result : C s2 d0

**6. Tapetex one-layer nonwoven of cellulosic and polyester fibres**

with a maximum weight of approx. 260 gr/m<sup>2</sup> (7.67 oz/sq/yd).

Test-report Warringtonfiregent : 18948A/B/C, dated May 9, 2018

Test-result : B s2 d0

**7. Tapetex multi-layer nonwoven of cellulosic and polyester fibres**

with a maximum weight of approx. 400 gr/m<sup>2</sup> (11.80 oz/sq/yd).

Test-report Warringtonfiregent : 18948D/E/F, dated May 9, 2018

Test-result : B s1 d0